

Standard Test Method for Indentation Hardness of Aluminum Alloys by Means of a Barcol Impressor¹

This standard is issued under the fixed designation B648; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscripted epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

^{e1} NOTE—Appendix X1 was moved to appear one page in October 2015.

1. Scope

1.1 This test method covers the determination of indentation hardness of aluminum alloys using a Barcol Impressor, Model No. 934-1.

1.2 The values stated in SI units are to be regarded as standard. No other units of measurement are included in this standard.

1.2.1 **Exception**—The values given in parentheses are for information only.

NOTE 1—Another model, No. 935, is for use on aluminum alloys. It is included in this test method and should not be used for aluminum alloys.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

- 2.1 *ASTM Standards*²
- E6 Terminology Relating to Methods of Mechanical Testing
 - E10 Test Method for Brinell Hardness of Metallic Materials
 - E18 Test Methods for Rockwell Hardness of Metallic Materials
 - E177 Practice for Use of the Terms Precision and Bias in ASTM Test Methods
 - E691 Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method

3. Terminology

3.1 **Definitions**—The definitions of terms relating to hardness testing appearing in Terminology E6 shall be considered

¹ This test method is under the jurisdiction of ASTM Committee B07 on Light Metals and Alloys and is the direct responsibility of Subcommittee B07.05 on Testing.

Current edition approved Oct. 1, 2015. Published October 2015. Originally approved in 1978. Last previous edition approved in 2010 as B648 – 10. DOI: 10.1520/B0648-10R15E01.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

as applying to the terms used in this test method.

4. Significance and Use

4.1 The Barcol Impressor is portable and therefore useful for in situ determination of the hardness of fabricated parts and individual test specimens for production control purposes.

4.2 This test method should be used only as cited in applicable material specifications.

5. Apparatus

5.1 **Barcol Impressor, Model 934-1**— See Fig. 1 and Fig. 2.

5.2 **Indentor**—The indentor shall consist of a hardened steel repeated cone having an angle of 26° with a flat tip 0.157 mm (0.0062 in.) in diameter. It shall fit into a hollow spindle and be held down by a spring-loaded plunger. See Fig. 2.

5.3 **Indicating Device**—The indicating dial shall have 100 divisions, each representing a depth of 0.0076 mm (0.00030 in.) penetration. The higher the reading, the harder the material.

6. Test Parts or Specimens

6.1 The testing area shall be smooth, clean, and free of mechanical damage. The surface may be lightly polished to eliminate scratches or die lines. It shall be such that it can be essentially perpendicular to the indentor during the test.

NOTE 2—The effect of curvature of the test specimen on the Barcol Impressor readings is presented in Appendix X1, Fig. X1.1.

6.2 **Dimensions**—Test parts or specimens shall be at least 1.5 mm ($\frac{1}{16}$ in.) thick and large enough to ensure a minimum distance of 3 mm ($\frac{1}{8}$ in.) in any direction from the indentor point to the edge.

7. Calibration

7.1 With the plunger upper guide backed out until it just engages the spring, place the impressor on a glass surface and press down until the penetrator point is forced all the way back into the lower plunger guide. The indicator should then read 100 ± 1 . If it does not, loosen the locknut and turn the lower plunger guide in or out to obtain a reading of 100.



FIG. 1 Barcol Impressor, Model 934-1

7.2 Read the hardness of a “hard” aluminum alloy reference disk supplied by the manufacturer of the impressor, if necessary, adjust so that the reading is within the range marked on the disk.

TABLE 1 Recommended Sample Sizes to Equalize the Variance of the Average

Hardness, M-934-1 Scale	Reading Variance	Coefficient of Variation, %	Variance of Average	Minimum Sample Size
50	1.66	1.1	0.02	5
60	1.39	0.9	0.02	5
70	1.12	0.8	0.02	4
80	0.85	0.7	0.02	3

7.3 Repeat the process with a “soft” reference disk.

7.4 If the reference readings cannot be obtained, subsequent measurements are not valid.

8. Procedure

8.1 Support the test parts or specimens on a hard firm surface if they are likely to bend or deform under the pressure of the indenter (Note 3). The indenter must be perpendicular to the surface being tested.

NOTE 3—Curved surfaces may be more difficult to support. When the load is applied, bending and spring action in the part or specimen should be avoided.

8.2 Grasp the impressor firmly between leg and point sleeve and set both on the surface to be tested. For irregular parts or small specimens this may require the impressor leg to be shimmed so that the indenter will be perpendicular to the test surface.

8.3 Quickly apply by hand sufficient pressure (4 to 7 kg, or 10 to 15 lb) on the housing to ensure firm contact with the test specimen and record the highest dial reading to the nearest 0.5 division (Note 4). Take care to avoid sliding or scraping while the indenter is in contact with the surface being tested.

NOTE 4—For relatively soft materials, the dial may indicate some drift toward lower numbers with time after the initial pressure. For this reason

it is recommended that readings be made quickly and that the highest observed value be used.

8.4 Impressions should not be made within 3 mm (1/8 in.) of the edge of the part or specimen or of other impressions.

9. Report

9.1 The report shall include the following:

9.1.1 Identification of material tested,

9.1.2 Model and serial number of impressor,

9.1.3 Number of readings taken,

9.1.4 Average of hardness values rounded to the nearest whole scale reading, and

9.1.5 Date of test.

10. Precision and Bias

10.1 The precision of this test method is based on an interlaboratory study of B648, conducted in 2008. Each of five laboratories tested a total of four alloys. Every test result represents the average of three individual determinations. Three test results (9 total test readings) from every laboratory were analyzed in order to determine the precision statistics listed below. Except for the limited number of replicates available from some laboratories, Practice E691 was followed for the design and analysis of the data; the details are given in ASTM Research Report No. B07-1002.³

10.1.1 **Repeatability limit (*r*)**—Two test results obtained within the same laboratory shall be judged not equivalent if they differ by more than the “*r*” value for that material; “*r*” is the interval representing the critical difference between two test results for the same material, obtained by the same operator using the same equipment on the same day in the same laboratory.

10.1.1.1 Repeatability limits are listed in Table 2.

10.1.2 **Reproducibility limit (*R*)**—Two test results shall be judged not equivalent if they differ by more than the “*R*” value for that material; “*R*” is the interval representing the critical difference between two test results for the same material, obtained by different operators using different equipment in different laboratories.

10.1.2.1 Reproducibility limits are listed in Table 2.

10.1.3 The above terms (repeatability limit and reproducibility limit) are used as specified in Practice E177.

10.1.4 Any judgment in accordance with 10.1.1 and 10.1.2 would normally have an approximate 95 % probability of being correct, however the precision statistics obtained in this ILS must not be treated as exact mathematical quantities which are applicable to all circumstances and uses. The limited number of materials tested, and laboratories reporting replicate results, guarantees that there will be times when differences greater than predicted by the ILS results will arise, sometimes with considerably greater or smaller frequency than the 95 % probability limit would imply. The repeatability limit and the reproducibility limit should be considered as general guides, and the associated probability of 95 % as only a rough indicator of what can be expected.

³ Supporting data have been filed at ASTM International Headquarters and may be obtained by requesting Research Report RR:B07-1002.




Diagram of Barcol Impressor
 TABLE 2 Hardness Instrument Scale Units

Material	Average ^a \bar{X}	Repeatability Standard Deviation s_r	Reproducibility Standard Deviation s_R	Repeatability Limit r	Reproducibility Limit R
3003-O2	80.282	0.57	1.314	1.671	3.678
5052-H32	73.784	0.69	0.562	1.197	1.574
6061-T6	83.347	1.55	1.379	1.879	3.862
7075-T6	92.211	0.92	0.74	1.461	2.075

^a The average of the laboratories' calculated averages.

10.2 Bias—At the time of the study, there was no accepted reference material suitable for determining the bias for this test method, therefore no statement on bias is being made.

10.3 The precision statement was determined through a statistical examination of 60 results, from five laboratories, on the four alloys described below.

- 3003-O2 - Alcoa Rolled Plate 0.250" x 12" x12" from 48" wide production
- 5052-H32- Alcoa Rolled Plate 0.250" x 12" x12" from 48" wide production
- 6061-T6 - Kaiser Rolled Plate 0.250" x 12" x12" from 48" wide production
- 7075-T6 - Kaiser Rolled Plate 0.250" x 12" x12" from 48" wide production

APPENDIX

(Nonmandatory Information)

X1. EFFECT OF CURVATURE OF TEST SPECIMEN ON BARCOL IMPRESSOR READINGS

X1.1 The effect of curvature on the results of Barcol Impressor tests on sheet is illustrated in Fig. X1.1.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned




FIG. X1.1 Effect of Curvature of Sheet on Barcol Impressor Readings—Model 934-1, 0.084-in. thick 2024-T3

in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend, if you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/